

Matador™ - 40 mil Coarse Texture - 6512

Issue Date: 7/9/2018 Version 1.1

DESCRIPTION

Matador™ 6512 is a 40 mil vinyl designed for reverse print graphic applications. The material has a coarse texture top surface and a smooth reverse surface for printing. Matador™ 6512 has passed ASTM D-2047 testing - which qualifies it to be designated as a slip resistant material.

APPLICATION

Matador™ 6512 is ideally suited for countertop mats, floor mats and other promotional graphics.

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	PSTC - 133 - Substrate	0.040 inch (0.900 mm)

PROPERTIES

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Coefficient of Friction (Static)	ASTM D-2047 Dry Leather	PASS
Service Temperature High	14 days at 220°F	No visible effects, moderate shrinkage and high elasticity
Low	14 days at -20°F	No visible effects
Texture	Top Surface Reverse Surface	Coarse Texture Smooth



CHEMICAL PROPERTIES	REAGENT	RECOMMENDATION
<u>Solvent Resistance</u> (Product laminated to stainless steel panel and allowed to condition for 24 hours at room temperature before testing. Sample was covered with reagent to the point that edges of product are also exposed to the reagent. The product is exposed to reagent for one hour at room temperature, then reagent is removed and product is immediately tested for scrape resistances, delaminating, and other visual effects.)	Water 10% Salt Water Bleach Trichloroethylene 25% Sulfuric Acid 1% Sodium Hydroxide Unleaded Gasoline Diesel Fuel Hydraulic Fluid 50% Antifreeze in water MEK Mineral Spirits 99% IPA	Recommended Recommended Recommended Not Recommended Intermittent Contact Only Recommended Recommended Recommended Recommended Recommended Not Recommended Recommended Recommended

Note: While the data contained herein is believed to be reliable averages of the product's properties, the data should not be used for specification purposes. Jessup Manufacturing cannot guarantee colors due to the variation in ink lots, manufacturing processes, etc. Sample colors may also vary as the samples may be shipped from different bundles or lots. Customers who desire specific performance data should contact Jessup Manufacturing Company for further recommendations.

WARRANTY

The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representations, guarantees or warranties of any kind are made to the accuracy or suitability for specific applications.