



# CatWalk®

Issue Date: 11/1/2015 Version 1.2

## DESCRIPTION

CatWalk® is a white, textured floor graphic media that can be applied indoors on various surfaces. It provides an extremely secure, slip resistant and chemical resistant surface and can make any image leap off the ground.

## APPLICATION

CatWalk® can be used on almost every surface, including tiles, marble, concrete, linoleum, porcelain, vinyl and more. It is designed for short to medium term use and is applicable on wet surfaces. Some uses are point-of-purchase, shopping malls, museums, supermarkets, pharmacies, showers and pool areas.

## PROPERTIES

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	PSTC - 133 - Substrate - Pressure Sensitive adhesive - Release Liner	0.018 inch (0.457 mm) 0.002 inch (0.051 mm) 0.007 inch (0.178 mm)
Peel Adhesion to:	PSTC – 101	
- Stainless Steel	15 minute dwell 24 hour dwell	55 oz/in (66 N/100 mm) 75 oz/in (82 N/100 mm)
- Powder coated surfaces *	15 minute dwell 24 hour dwell	40 oz/in (44 N/100 mm) 55 oz/in (60 N/100mm)
- Polyethylene	15 minute dwell 24 hour dwell	20 oz/in (22 N/100 mm) 25 oz/in (27 N/100 mm)
Shear Adhesion to:	PSTC – 107	
- Stainless Steel	1/2" x 1/2" x 1000g	<5 hours

\* Color and lot variances of coated surfaces including paints, powder coatings, lacquers, stains, and other treatments may vary the performance of the tape and should be evaluated for the compatibility of the tape to the specific surface.

**PROPERTIES**

<b>PHYSICAL PROPERTIES</b>	<b>TEST METHODS</b>	<b>AVERAGE RESULTS</b>
Coefficient of Friction (Static)	ASTM D-2047	0.62
Tack	PSTC - 6 Rolling Ball Tack	< 5 inches
Service Temperature High Low	14 days at 220°F 14 days at -20°F	No visible effects No visible effects
<b>CHEMICAL PROPERTIES</b>	<b>REAGENT</b>	<b>RECOMMENDATION</b>
<u>Solvent Resistance</u> <i>(Product laminated to stainless steel panel and allowed to condition for 24 hours at room temperature before testing. Sample was covered with reagent to the point that edges of product are also exposed to the reagent. The product is exposed to reagent for one hour at room temperature, then reagent is removed and product is immediately tested for scrape resistances, delaminating, and other visual effects.)</i>	Water 10% Salt Water Bleach Trichloroethylene 25% Sulfuric Acid 1% Sodium Hydroxide Unleaded Gasoline Diesel Fuel Hydraulic Fluid 50% Antifreeze in water MEK Mineral Spirits 99% IPA	Recommended Recommended Recommended Not Recommended Intermittent Contact Only Recommended Recommended Recommended Recommended Recommended Not Recommended Recommended Recommended

**Note:** While the data contained herein is believed to be reliable averages of the product's properties, the data should not be used for specification purposes. Customers who desire specific performance data should contact Jessup Manufacturing Company for further recommendations.

**WARRANTY**

The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representations, guarantees or warranties of any kind are made to the accuracy or suitability for specific applications.